

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
8 November 2007 (08.11.2007)

PCT

(10) International Publication Number
WO 2007/126783 A1

(51) International Patent Classification:
B65D 81/38 (2006.01)

(21) International Application Number:
PCT/US2007/007521

(22) International Filing Date: 27 March 2007 (27.03.2007)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
60/789,297 3 April 2006 (03.04.2006) US

(71) Applicant (for all designated States except US): **LBP MANUFACTURING, INC.** [US/US]; 1325 South Cicero Avenue, Cicero, IL 60804 (US).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **FU, Thomas** [US/US]; 879 Blackpine Drive, Milford, OH 45150 (US). **COOK, Matthew, R.** [US/US]; 29 West Birchwood Avenue, Hinsdale, IL 60521 (US). **NOBERS, John** [US/US]; 742 Mitchell Avenue, Elmhurst, IL 60126 (US).

(74) Agent: **GNOFFO, Vincent, J.**; Brinks Hofer Gilson & Lione, P.o. Box 10087, Chicago, IL 60610 (US).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RS, RU, SC, SD, SE, SG, SK, SL, SM, SV, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.


(81) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LT, LU, LV, MC, MT, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

- with international search report
- before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: THERMALLY ACTIVATABLE INSULATING PACKAGING



(57) Abstract: A package or container includes a side wall, the side wall having an inner surface and an outer surface. At least one of the inner surface or the outer surface of the side wall may be at least partially coated by a layer of a thermally expandable material. The material may be adapted to be expanded to provide thermal insulation.

WO 2007/126783 A1

THERMALLY ACTIVATABLE INSULATING PACKAGING

RELATED APPLICATION

[0001] The present patent application claims the benefit of the filing date under 35 U.S.C. §119(e) of Provisional U.S. Patent Application Serial No. 60/789,297, filed April 3, 2006, which is hereby incorporated by reference.

BACKGROUND

[0002] Consumers frequently purchase ready-made products, such as food and beverages, in disposable containers. Thermally insulated containers may be designed for hot or cold liquids or foods, such as hot coffee, iced-tea, or pizza. These containers may maintain the temperature of the liquid or food contents by preventing heat or cold transfer from the contents to the consumer's hand.

BRIEF SUMMARY

[0003] A package or container includes a side wall, the side wall having an inner surface and an outer surface. At least one of the inner surface or the outer surface of the side wall may be at least partially coated by a layer of a thermally expandable material. The material may be adapted to be expanded to provide thermal insulation.

[0004] Other systems, methods, features and advantages of the invention will be, or will become, apparent to one with skill in the art upon examination of the following figures and detailed description. It is intended that all such additional systems, methods, features and advantages be included within this description, be within the scope of the invention, and be protected by the following claims.

BRIEF DESCRIPTION OF THE DRAWINGS

[0005] FIG. 1 is a perspective view of a cup assembled with a die cut blank.

[0006] FIG. 2 is a perspective view of a cup assembled with a full-body die cut blank with openings.

[0007] FIG. 3 is a perspective view of another integrated container with channels.

- [0008] FIG. 4 is a cross section view of an assembled die cut blank.
- [0009] FIG. 5 is a top perspective view of a cross section of a cup assembled with a die cut blank.
- [0010] FIG. 6 is a view of a die cut blank disassembled from a cup.
- [0011] FIG. 7 is a view of a die cut blank disassembled from a cup.
- [0012] FIG. 8 is a view of a die cut blank disassembled from a cup.
- [0013] FIG. 9 is a view of a die cut blank disassembled from a cup.
- [0014] FIG. 10 is a view of a die cut blank disassembled from a cup.
- [0015] FIG. 11 is a view of a die cut blank disassembled from a cup.
- [0016] FIG. 12 is a view of a cup assembled with a die cut blank illustrating heat transfer.
- [0017] Fig. 13 is a side cutaway view of a double-wall cup.
- [0018] Fig. 14 is a block diagram of an exemplary process for applying a micro-particle coating to substrates.
- [0019] Fig. 15 is a schematic of applying a coating to a substrate with spray nozzles.
- [0020] Fig. 16 is a schematic of applying a coating to a substrate with non-spray nozzles.

DETAILED DESCRIPTION

[0021] A package or container may be constructed of, and/or insulated with, a die cut blank, such as a sleeve. The die cut blank may be fixed to a container or it may be removable. Thermally-expandable material may be applied to the container and/or die cut blank. Expandable materials that are expanded in ways other than by temperature may also be used. The material may be expanded before reaching an end user, such as when the container and/or die cut blank are manufactured, and/or the material may be expanded only on end use and only in response to a determined temperature. The material may be used to aid with insulating capabilities of the container and/or die cut blank, and/or to add rigidity to the container and/or the die cut blank, such as to reduce a thickness of the material components of container and/or die cut blank.

[0022] FIG.1 illustrates a container **101**, such as a cup, and a die cut blank **102**, such as a sleeve. The container is described in terms of a cup, for example, but may also include other containers such as a plate or tub. The blank may be in the form of a container sleeve or an outer wall to the container. The container is not limited to a cup and may be any other container, including but not limited to, a bulk coffee container, a soup tub, and press-formed containers, with or without covers or sleeves. The container **101** may be a cylindrical cup or a container having other geometrical configurations, including conical, rectangular, etc. The die cut blank is not limited to a corrugated die cut blank, and may be constructed of paperboard, paper, etc. The die cut blank **102** may be made of any nominal paper stock, including but not limited to, natural single-face, white-topped single face, coated bleached top single-face, corrugate, fluted corrugate or any combination of these. The die cut blank **102** may be removable from the container or the die cut blank may be adhered to the container **101**. The blank **102** may be adhered, for example, by laminating the die cut blank onto the container, using a hot melt, cold melt and/or any other adhesive or sealing mechanisms.

Alternatively or in addition, the blank may be adhered with an expandable material, such as a microsphere material. If the die cut blank is attached to the cup during manufacture, it may increase efficiency by eliminating an assembly step by the commercial end-user. Further, it may decrease the amount of storage space required by the commercial end-user, e.g., storing one item as opposed to two.

[0023] FIG. 1 is not necessarily drawn to scale. For example, the die cut blank **102** may cover a larger or smaller portion of the container's **101** surface than illustrated. For example, the die cut blank may provide full body coverage.

Increasing the surface area of the die cut blank **102** may provide a larger insulated area as well as a larger print surface. Although the drawing illustrates the die cut blank on a cup, the die cut blank may be added to any other containers, such as but not limited to, a bulk beverage container, press-formed container, and soup tub.

[0024] A thermally activatable coating may be applied between the container **101** and the blank **102**. The expandable material may be thermally-activatable, by a hot or cold temperature, and may be an expandable coating or adhesive,

including but not limited to, binder, expandable microspheres or other micro-encapsulated particles, pigment and other additives, or any combination of these or other materials. The material may be expandable when wet or dry. The material may include any synthetic or natural material including aqueous based, solvent based, high solids, or 100% solid materials. The amount of solid content is typically 30% to 80% of the material, and more preferably 40% to 70%. Additional ingredients may be added to the binder, including but not limited to, pigments or dyes, fillers/extenders, surfactants for dispersion, thickeners or solvents to control viscosity for optimized application, defoaming agents, additives like waxes or slip aids, etc. Alternatively, the binder may be an adhesive. The expandable material may have several properties, including but not limited to thermal insulation to keep container contents hot or cold, and/or it may expand on contact with hot material (such as, over 150 °F), and preferably remains inactive before a determined designed activation temperature, such as at about room temperatures. The coating may be repulpable, recyclable, and/or biodegradable.

[0025] FIGS. 2 and 3 illustrate a container **101** with an outer wall of a die cut blank **102**. The container **101** may be constructed as a double-wall cup assembly. The container **101** may be a cylindrical cup or container having other geometrical configurations, including conical, rectangular, etc. The die cut blank may fully or partially cover the body of the container. The die cut blank **102** may be an outer wall of the container **101**. The container **101** and die cut blank **102** may be integrated into a cup **100** and the expandable material or adhesive may be applied between the container body **101** and the die cut blank **102**. The activatable material may additionally have adhesive properties and thus may form the only attachment between the container and the blank. The die cut blank **102** may be made of any nominal paper stock, including but not limited to, natural single-face, white-topped single face, coated bleached top single-face or any combination of these. The die cut blank and/or container may be repulpable, recyclable and/or biodegradable. The die cut blank **102** may include, for example, corrugated, flute

corrugated or embossed grooves. The grooves may be in a vertical, diagonal, or other direction and may channel heat away from the hands.

[0026] The die cut blank **102** may be removable from the container or the die cut blank may be adhered to the container. For example, a one-piece container, such as a cup, may be manufactured **101** by laminating the die cut blank onto the container, using a hot melt and expandable material to secure the die cut blank, or any other adhesive or sealing method. Alternatively, the thermally-activated material may be used to adhere the blank to the cup. If the die cut blank **102** is permanently attached to the container **101** during manufacture (e.g., creating an integrated one-piece cup), it may increase the efficiency of using a thermal die cut blank by eliminating an assembly step by the commercial end-user. Further, it may decrease the amount of storage space required by the commercial end-user, e.g., storing one item as opposed to two.

[0027] The die cut blank may remain open ended on one side or on opposing sides, which may permit airflow. For example, in FIG. 2, the container may contain openings **210** near the top **212** of the integrated container **100**. The opening may be formed into the die cut blank, for example as holes, and the air flow may be created when the space between the container **101** and the die cut blank **102** is expanded by the expandable material. Airflow may be further manipulated, for example, upward and away from the holding fingers by corrugated, flute corrugated, or other channels in the die cut blank **102** or expandable material application pattern **216**. For example, the pattern of application of the expandable material may create heat release channels **216**.

[0028] FIG. 3 illustrates an alternate non-limiting example of how application of the expandable material may form openings **310** near the top **212** of the container **101**. The channels may be formed on expansion of the material. There may be openings on opposing ends of the container **101**, such as at the top **212** and the bottom **214**. The openings may be formed by wrapping the die cut blank on the container without completing the seal at the top **212** or bottom **214**.

[0029] FIG. 4 illustrates a cross section of a die cut blank **102** assembled with the cup **101**. This figure is meant to be illustrative and not limiting. The cup may

be replaced with any container, for example, a press-formed tray, a soup tub, or a bulk beverage container. The die cut blank **102** may have an inner face **406** and an outer face **404**. An expandable material may be applied to the inner face **406**, the outer face, **404** and/or to a surface between **402** the inner face **406** and the outer face **404**. The inner face **406** and outer face **404** do not necessarily contain a space **402** between. In another non-limiting example, the expandable material may be applied between the container wall **101** and the die cut blank **102** and may result in an integrated container **100**.

[0030] A thermally-expandable material **408** may be applied to an inner face **406** of the die cut blank **102** in an inactive form. The inactivated material **408** may be applied as a thin film that does not materially alter the thickness of the die cut blank **102**. Applying the expandable material to the inside of the die cut blank may also maintain the printability of the outer face of the die cut blank. If the inactivated expandable material **408** on the die cut blank **102** is assembled, for example, with a standard paper cup, it may maintain the slim profile of the cup. Maintenance of the slim profile may retain the efficient nesting qualities of a standard cup, allowing it to be efficiently cased, crated and shipped.

[0031] The expandable material **408** may be activated and thereby expanded by, for example, adding hot liquid, beverage or food into the container **101**. Activation may occur only at the consumption stage and not at the processing stage of the die cut blank, such that the die cut blank may be shipped to the consumer with a substantially inactivated expandable material. For example, the activation point of the expandable material may be greater than about 120 °F and/or less than 60 °F, such that the expandable material may be activated only by the temperature of hot liquids, beverages, or food and not activated by ambient or body temperature. The activation may cause the expandable material to expand and “push back” the die cut blank **102** from the container **101** creating an increased air gap. The air gap may create a thermal barrier between the hot beverage container **101** and the hand of the consumer. The activation may also enhance the stiffness and/or rigidity of the container, which may allow for a reduction in the material or thickness of the container wall. As described in more

detail below, the coating may also be activated, or at least partially activated, before reaching the consumer.

[0032] The expandable material **408** may be applied to the die cut blank **102** in an unexpanded state. Expansion of the die cut blank may not occur until activated by adding hot fluid or solids, such as at the point of serving. This may be different from expanding the material during manufacture of the die cut blank. Expansion during manufacture may increase the bulk of the die cut blank. The expandable material may be controlled to effect nesting efficiency. The properties of the die cut blank may be further controlled by, for example but not limited to, combining a die cut blank constructed from fluted corrugate material with patterned application of expanded material to provide specific insulation, air flow characteristics and container rigidity enhancement. For example, the corrugation and/or the pattern of expandable material applied to the die cut blank may direct heat convection upward, and may therefore reduce heat transfer horizontally toward the holding hand of consumer. In other implementations, expansion may occur before shipping, such as before, during or after the manufacturing of the container.

[0033] FIG. 5 is an exemplary top view of a cross-section of a container **101** assembled with a thermal die cut blank **102**. This figure is illustrative only and not limiting. The expandable material **408** may be applied to the inner-face **406** of the die cut blank **102**. For example, the expandable material **408** may be applied between the die cut blank **102** and the wall of the container **101** and may form an integrated two-layer cup with thermally-activatable insulated expandable material in between. The expandable material may include, for example, expandable microspheres **502** dispersed in a binder or any other suitable material disclosed above **504** and may include an adhesive property.

[0034] FIG. 6 illustrates an exemplary die cut blank **602**. This drawing is illustrative and not meant to be limited to a size or shape. The size and shape may be adapted to the dimensions of any container. An expandable material **408** may be applied to the die cut blank **602**. The expandable material may be applied by a number of methods, such as but not limited to, a nozzle spray gun, printing, a slot

coater, or other methods, such as those described in more detail below. The expandable material **408** may be applied to the die cut blank **602**, for example, on an in-line cup wrapping machine, in-line on a folder/gluer, or by other suitable methods, such as off-line coating and drying. The expandable material **408** may be applied to the die cut blank **602** in any suitable pattern, such as but not limited to, banded, dotted, waved, squares, circles, diamonds, random, a combination of these or any other pattern. For example, the expandable material may be applied in a pattern that manipulates air flow and/or conducts heat, for example, vertically upward away from the holding fingers. The expandable material may be applied such that it forms channels, or expands to form channels on activation. The channels may direct the natural convection. The expandable material **408** may fully or only partially cover the surface being coated.

[0035] The coated die cut blank may be removably or permanently attached to a container or cup by, for example, wrapping the die cut blank around the container. For example, a one-piece cup or container may be manufactured **101** by laminating the die cut blank onto the container, using a hot melt and expandable material to secure the die cut blank, using an expandable material with adhesive properties, a combination of these or any other adhesive or sealing method. If the die cut blank **102** is permanently attached to the container **101** during manufacture (for example, creating an integrated one-piece cup), it may increase the efficiency of using a thermal die cut blank by eliminating an assembly step by the commercial end-user. Further, it may decrease the amount of storage space required by the commercial end-user (storing one item as opposed to two). The shape of the die cut blank in the drawing is not meant to be limiting. The shape of the die cut blank may be adapted to the shape of other containers, for example but not limited to, a soup tub, press-formed container, or bulk beverage containers.

[0036] The die cut blank **602** may, optionally, contain in-seam hot-melt **604** or cold-set glue. If the expandable material **408** is also an adhesive, the in-seam hot-melt or cold-set **604** may be omitted. The in-seam hot-melt/cold-set glue **604** may be used in addition to the expandable material **408**, such as, for bonding

reinforcement. The die cut blank may be applied to a cup by, for example, wrapping, laminating, or other manufacturing processes.

[0037] FIGS. 7 through 11 illustrate other examples of a die cut blank **402**. These examples are merely illustrative and not limiting. FIG. 7 illustrates a die cut blank **602** with expandable material **408** applied in a pattern **709** to channel the release of heat. The die cut blank **602** may be made of, for example, corrugated paper, such as but not limited to fluted corrugate. Convection may be manipulated by corrugation, the pattern of application of the expandable material, or in another suitable manner.

[0038] FIGS. 8 through 11 illustrate other possible, non-limiting examples of potential patterns of expandable material. The patterns of expandable material are represented by numbers **809**, **909**, **1009**, and **1109**, respectively. The expandable material may be applied in patterns other than those illustrated in FIGS. 7-11. The pattern of expandable material **809**, **909**, **1009**, and **1109**, respectively, may vary in thickness and may provide graduated flow to channel heat to die cut openings. Die cut openings are represented by numbers **814**, **912**, **1012**, and **1112**, respectively. Die cut openings may also be located and/or include shapes such as illustrated by numbers **812**, **914**, **1014**, and **1114**. There may be die cut openings at opposing ends of the blank, or only at one end. The shapes of the die cut openings in Figs. 8-11 are illustrative only and not limiting. For example, the patterns of expandable material and the shape of the die cut openings may be so arranged as to manipulate air flow, for example but not limited to, creating a Venturi effect.

[0039] FIG. 12 is an illustrative example showing exemplary heat transfer. This example is not meant to be limiting, but merely illustrative of possible heat loss manipulation. Total heat loss of the system may be represented by the following equation:

$$Q^T \text{ [Cal./second]} = Q_1 + Q_2 + Q_3 + Q_4$$


Where Q^T is the total heat loss. Q_1 **1204** may be the heat loss due to water evaporation. Q_2 , Q_3 , and Q_4 , represented by **1202**, **1206**, and **1208**, respectively, may represent the convectational and conductional heat loss.

[0040] The objective of keeping contents hot may be achieved by minimizing Q^T . The die cut blank may minimize Q^T by minimizing Q_2 , Q_3 , and Q_4 . The low thermal conductivity of the expandable material may result in much lower heat loss due to Q_2 , Q_3 , and Q_4 .

[0041] The objective of preventing consumer flesh burns may be achieved by, for example, minimizing Q_2 , Q_3 , and Q_4 , especially Q_2 , Q_3 , while allowing Q_1 and Q_4 to channel the unavoidable high heat flux (due to the hot liquid) vertically up or down. This may be achieved by, for example, adding corrugated grooves to the die cut blank. The grooves may be, for example, in a generally vertical or diagonally tilted.

[0042] Non-limiting examples follow.

[0043] Example 1. Example 1 provides a graphical representation of how the expandable material may alter thermal conductivity. The temperature on the inside of a cup may be represented by T_i . The temperature on the outside of the cup may be represented by T_o . The top line, X, may represent a container without the coated die cut blank. The second line, Y, may represent a container assembled with a coated die cut blank. This example may illustrate that, in a container without a die cut blank coated with the expandable material, the difference in the temperature inside versus the outside of the container may be very small. In a container with a die cut blank coated with the temperature activated material, the difference in the temperature between inside and outside may be small when the hot food or beverage is added to the container. However, the food or beverage may activate the material, A, on contact, causing the material to expand. When the material expands, the difference in temperature $T_i - T_o$, may increase.



[0044] Example 2. Example 2 illustrates temperature sensory comparison of various die cut blank materials coated with the thermally-expandable material compared to without the thermally-expandable material. The following experiment is for illustration only and is not limiting, other experimental results might be obtained.

[0045] A thermally, or other, expandable material may be applied to die cut blanks made of various materials, such as but not limited to paper, paperboard, and fluted corrugated paper. Each die cut blank may be wrapped around a container, such as a cup. The cup may be filled with hot water. The cups may then be handled with bare hands and a comparison made between the sensory responses to the two conditions. In each test, the cups with coated die cut blanks were less “hot” to the touch than those with uncoated die cut blanks. Expansion occurred within a few minutes of pouring hot water into the cup.

[0046] Example 3. Coatings may be applied by smearing the coating to a single face medium. The coating may be expanded when wet using a MASTER-MITE 120 V, 475 W heat gun at 600 degrees F.

[0047] Example 4. Coatings may be applied to the outside of a 12 Oz cup and allowed to air-dry overnight. The next day, 190 degree F hot water may be poured into the cup. Noticeable expansion may be observed shortly after filling the 190 degree F hot water into the cup. Lids may be placed on the cup, and after 7

minutes more expansion may be observed, but still partial expansion. A benefit of post-heat activation may be that the hotter the liquid the more the coating expands.

[0048] Example 5. Coating was applied to a cup. A 250 W IR heater manufactured by Fisher Scientific model no. 11-504-50 may be used to heat the coating. Expansion may be slow when the lamp is six inches away from the coating and immediate when one inch away from the coating. Excess heat and time may cause coating deformation from the substrate surface.

[0049] Example 6. Coating may be applied to paper, which may then be wrapped around a paper cup after the coating is allowed to air dry. Heat from a heat gun may be used to heat the part of the coating indirectly through the paper shell for one minute. The coating expanded. Another part of the unheated coating may be heated under an IR lamp through the paper. The coating expanded.

[0050] Fig. 13 is a side cutaway view of a double wall container **101**. The double wall container **101** may provide a jacket of air between an outer wall **1300** and contents **1302**, such as a hot or cold beverage or food, of the container **101**. The air jacket may provide thermal insulation as measured by an outside surface temperature T_0 . The air jacket may partially or completely surround the container **101**. When the container **101** is grabbed, a pressure exerted on the outer wall **1300** may act to collapse the outer wall **1300** at pressure points to reduce the air jacket and potentially initiate contact with an inner wall **1304** of the container **101**. The air jacket may collapse under pressure points and may give a sense of low rigidity, and the contact may create hot spots on the outer wall **1300** if a thermally expandable coating **216** is not used.

[0051] If a sufficient amount of coating **216** is used, the coating **216** may act to provide rigidity without compromising the thermal insulation of the air jacket to the outer wall **1300** such that the outer wall **1300** does not collapse, completely or partially. The coating **216** may add mechanical strength to the container **101**. Lighter weight materials may be used to produce the container **101** due to mechanical strength added by the coating **216**, such that the source of a substrate forming the container **101** may be reduced. The coating **101** may be applied in spots, such as dots, or another pattern, either on the inner wall **1304**, the outer wall

1300, or both, such that the coating **216** provides an air gap and prevents the container **101** from collapsing under holding pressure. The coating **101** may also provide a rigid feel to the user, while allowing a reduction of the substrate material.

[0052] Fig. 14 is a block diagram of an exemplary process for applying a micro-particle coating to substrates. The process may include applying a microsphere or other expandable coating to any of a substrate, die cut blank, container, sleeve, catering trays, double-wall cups, press-formed tray, soup tub and bag-in-the box containers. The process may include inline **1400** and off-line **1410** procedures. The inline procedure **1400** may include stacking stations **1420**, manufacturing stations **1430**, and packaging stations **1440** used for the manufacturing of the container from paper or die cut stock. The stacking, manufacturing and packaging stations may be completely automated and/or include manual stations.

[0053] Coating application processes may occur in-line **1400** or offline **1410**, at the same or another facility. In-line application may include the application of the coating at one or more of the stacking stations **1420**, manufacturing stations **1430**, and packaging stations **1440**. The coating may be applied in various ways, including but not limited to brushes, sponges, printing, a nozzle, spray, and a slot die coater. Any of these applications, or various combinations of them, may occur in-line **1400** or offline **1410**, where the off-line process may occur before the stacking stage **1420**.

[0054] Application with a brush or brushes may occur by feeding the coating with pressure through a tube to the brush. The brush may be manufactured from different materials such as horse hair or synthetic materials. The brush may include hollow filaments such that the coating is applied through the filaments. The brush may apply a swatch or pattern of the coating. The amount of coating to the brush may be controlled such that the amount of coating applied to the substrate may be metered. As an illustrative and not limiting example, the amount may be controlled such that a 1/64th inch layer of coating is applied, which may expand to 1/16 or 1/32 of an inch, or the distance of the gap between an inner and

outer layer of a double-wall cup. It may be preferable that the coating does not deform a shape of the outer layer once expanded. The coating may be distributed in a uniform or varying pattern. The brush may be used for broader applications, such as to coat the inside of a bag-in-the-box container.

[0055] Application with a printing press may occur by running substrates through rollers. The substrates may be roll or web form of paper stock, or alternatively in sheet form. The coating may be press applied in spots or patterns or with full coverage, depending on an implementation.

[0056] In Fig. 15, spray nozzles **1500** may be used to apply a coating **1510** to a substrate **1520**. The nozzles may diffuse the coating to apply a thin, uniform layers of the coating on the substrate. One or more spray nozzles may be used to form continuous or interrupted patterns of the coating. The nozzles may be arranged such that the applied coatings overlap, are side-by-side and/or are separated by a space. The spray may be metered to control a thickness of the applied coating. The nozzle may also be positioned to direct spray of the coating onto designated portions of the substrate, such as at a corner.

[0057] In Fig. 16, non-spray nozzles **1600** may be used to apply a stream **1610** of coating to the substrate **1620**. The stream may be metered through the nozzle to apply a precise amount. The nozzle may be sized to control a specified width and height of the stream **1610**. Flow from the nozzles may be turned on and off to accommodate a specified pattern of the coating to the substrate.

[0058] In a trough or a dip coating application, substrates may be moved through the trough that contains coating material. One or both sides of the substrate may be run through the trough. A thickness of the coating being applied to the trough may be controlled by how long the substrate sits in the material. A temperature of the coating and substrate may be controlled to activate or not activate the expandable coating during the coating process. A control blade may be used to meter off excess coating. The substrates may be belt fed through the trough or individually held in the through.

[0059] With any of the above application processes, and with any other process, the applied coating may be dried or set, such as by applying or blowing

cool air or warm air without activating the coating, if it is desired to expand the coating in a later process, such as during manufacturing or at the time of consumer use. The coating may also be expanded after manufacturing and before consumer use, such as at the stacking station 1440. The coating may be expanded before or after stacking the containers.

[0060] Coated or uncoated blanks may be fed to the staking station 1420. The coating may be applied during in-line or off-line processing. If applied in-line, the coating may be allowed to dry before the cups, sleeves, containers, etc. are formed, or they may be formed while the coating is wet. Depending on the properties of the coating, it may take a couple of seconds to several minutes to dry. The coating may be activated during the in-line manufacturing or afterwards, such as at the consumer stage. To activate the coating in-line, any or all of infrared (IR), air, convection or conductive heating methods may be used. The coating may take a couple of seconds to several minutes to fully expand. For example, a mandrel, which holds a container from the inside of the container, and/or a collar, which holds a cup from the outside of the container, may be used to apply heat to expand the coating during the container manufacturing process. If a wet or partially dry coating contacts the mandrel during process, the mandrel may be manufactured to include a non-stick material, such as TEFLON to prevent sticking or transfer of the coating onto the mandrel. Lower activation temperatures may be preferred if the activation occurs in-line. By activating the coating, the coating expands to form a reinforced air gap. The coating may be partially expanded during manufacturing of the container, and then the expansion may continue to the consumption stage.

[0061] As mentioned, use of the coating may help to reduce the thickness of substrate needed to make the container, sleeves, etc., while maintaining a better rigid feel to the consumer. The coating may also improve insulation properties of the container, and to help keep the beverages or foods warm or cold longer, depending on the application. The substrates may be made of natural fibers, synthetic or both, such as SBS (solid bleached sulfate) paper board or box board. A sleeve materials, such as liner and medium, may be produced of 15LB/3000ft²

to 100LB/3000ft² material, and preferably 18LB/3000ft² to 50LB/3000ft². The caliper of the paper substrate for hot or cold cups, soup tub, press-formed container and other non-corrugated containers may range from 9 point to 24 point, and preferably 10 point to 24 point, where a point is equal to 1/1000 inch.

[0062] While various embodiments of the invention have been described, it will be apparent to those of ordinary skill in the art that many more embodiments and implementations are possible that are within the scope of the invention.

WE CLAIM:

1. A double-wall container, comprising:
 - an inner wall;
 - an outer wall attached to the inner wall, where the inner wall and the outer wall form an air gap therebetween; and
 - and expandable coating positioned between the inner wall and the outer wall.
2. The double-wall container of claim 1 where the expandable coating comprises expandable microspheres.
3. The double-wall container of claim 1 where the expandable coating provides thermo insulation between the inner wall and the outer wall.
4. The double-wall container of claim 1 where the expandable coating provides a rigidity to the outer wall.
5. The double-wall container of claim 1 where the outer wall is comprised of a paper stock.
6. The double-wall container of claim 5 where the expandable coating accommodates a reduction in a weight of the paper stock.
7. The double-wall container of claim 1 where the expandable coating is activated to expand by a hot temperature.
8. The double-wall container of claim 1 where the expandable coating is applied is a dotted pattern.
9. A method of making a double-wall container, comprising:
 - providing a first substrate to form a container;
 - providing a second substrate to form an outer wall of the container;
 - coating the second substrate with a thermally expandable material;
 - attaching the second substrate to the container to form the outer wall;
 - forming the double-wall cup from the container and the outer wall;
 - and
 - applying the expandable coating between the container and the outer wall.
10. The method of claim 9 where the expandable coating is applied before forming the double-wall cup.

11. The method of claim 9 where the expandable coating is applied during the forming of the double-wall cup.
12. The method of claim 9 further comprising expanding the expandable coating during the forming of the double-wall cup.
13. The method of claim 9 further comprising expanding the expandable coating after forming the double-wall cup.
14. The method of claim 9 where the coating is applied is a dotted pattern.
15. A container, comprising:
 - a side wall having an inner surface and an outer surface;
 - at least one of the inner surface or the outer surface of the side wall being at least partially coated by a layer of an expandable material; and
 - the material adapted to be expanded to provide thermal insulation.
16. The container of claim 15, where the expandable material comprises expandable microspheres.
17. The container of claim 15 where the side wall comprises the side of a sleeve for a cup.
18. The container of claim 15 where the side wall comprises the side of a container for holding a bag.
19. The container of claim 15 where the material is expanded upon manufacturing.
20. The container of claim 15 where the material is expanded by a beverage or food.
21. The container of claim 15 where the expandable material is thermally expandable.

1/8




Fig. 1




Fig. 2

2/8




Fig. 3




Fig. 4

3/8




Fig. 5




Fig. 6

4/8




Fig. 7






Fig. 8

5/8



6/8




Fig. 11








Fig. 12

7/8



8/8



INTERNATIONAL SEARCH REPORT

International application No
PCT/US2007/007521

A. CLASSIFICATION OF SUBJECT MATTER
INV. B65D81/38

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
B65D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 6 257 485 B1 (SADLER CLAUD E [US] ET AL) 10 July 2001 (2001-07-10) column 12, line 35 - column 13, line 30; figures 2A,4A	1-7,9, 10,13, 15-18,21
X	US 2002/172818 A1 (DEBRAAL JOHN CHARLES [US] ET AL) 21 November 2002 (2002-11-21) paragraphs [0025], [0063] - [0098]	1-10, 14-18,21
A	US 5 145 107 A (SILVER VIRGINIA K [US] ET AL) 8 September 1992 (1992-09-08) abstract	1-21

☐ Further documents are listed in the continuation of Box C.

☒ See patent family annex.

* Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *G* document member of the same patent family

Date of the actual completion of the international search

3 September 2007

Date of mailing of the international search report

13/09/2007

Name and mailing address of the ISA/

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Jervelund, Niels

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/US2007/007521

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 6257485	B1	10-07-2001	US 2001013537 A1	16-08-2001
US 2002172818	A1	21-11-2002	NONE	
US 5145107	A	08-09-1992	NONE	